

RES-135 20/5 KROM ALÜMİNYUM YUVARLAK TEL

°C Ct	100 1	200 1,01	300 1,01	400 1,02	500 1,03	600 1,14	700 1,05	800 1,06	900 1,07	1100 1,07	1200
Çap	mm ²			ohm/mt (20°C)			Gr/mt				
6,000	28,26000			0,0478			223,4000				
5,000	19,62500			0,0688			155,1000				
4,500	15,89630			0,0849			125,6000				
4,000	12,56000			0,1074			99,3000				
3,500	9,61630			0,1403			75,9900				
3,250	8,29160			0,1627			65,5300				
3,000	7,06500			0,1910			55,9300				
2,800	6,15440			0,2192			48,6400				
2,500	4,90630			0,2750			38,7700				
2,250	3,97410			0,3395			31,4100				
2,000	3,14000			0,4297			24,8200				
1,900	2,83390			0,4761			22,4000				
1,800	2,54340			0,5305			20,1000				
1,700	2,26870			0,5948			17,9300				
1,600	2,00960			0,6714			15,8800				
1,500	1,76630			0,7639			13,9600				
1,400	1,53860			0,8770			12,1600				
1,300	1,32670			1,0171			10,4900				
1,200	1,13040			1,2189			8,9990				
1,100	0,94990			1,4206			7,5080				
1,000	0,78500			1,7189			6,2030				
0,950	0,70850			1,9046			5,5990				
0,900	0,63590			2,1221			5,0250				
0,850	0,56720			2,3791			4,4820				
0,800	0,50240			2,6857			3,9710				
0,750	0,44160			3,0558			3,4900				
0,700	0,38470			3,5079			3,0400				
0,650	0,33170			4,0683			2,6210				
0,600	0,28260			4,7746			2,2340				
0,550	0,23750			5,6822			1,8770				
0,500	0,19630			6,8755			1,5510				
0,475	0,18090			7,6183			1,4000				
0,450	0,15900			8,4883			1,2560				
0,425	0,13850			9,5163			1,1210				
0,400	0,12560			10,7430			0,9930				
0,375	0,11340			12,2230			0,8726				
0,350	0,09620			14,0320			0,7599				
0,320	0,08040			16,7860			0,6353				
0,300	0,07070			19,0990			0,5583				
0,280	0,06150			21,9240			0,4864				
0,250	0,04910			27,5020			0,3877				
0,240	0,04520			29,8420			0,3574				
0,220	0,03800			35,5140			0,3003				
0,200	0,03140			42,9720			0,2482				
0,190	0,02840			47,6140			0,2240				
0,180	0,02540			53,0520			0,2010				
0,170	0,02270			59,4770			0,1793				
0,160	0,02010			67,1430			0,1588				
0,150	0,01770			76,3940			0,1396				
0,140	0,01540			87,6980			0,1216				
0,130	0,01330			101,7100			0,1049				
0,120	0,01130			119,3700			0,0893				
0,110	0,00950			142,0600			0,7510				
0,100	0,00790			171,8900			0,0620				

çalışma sıcaklığındaki direnci bulmak için "Ct" katsayısı ile 20°C deki ohm direncini çarpınız