

RES-70 70/30 NİKEL KROM YUVARLAK TEL

°C	100	200	300	400	500	600	700	800	900	1100	1200
Ct	1,01	1,02	1,03	1,05	1,05	1,05	1,05	1,05	1,06	1,06	1,07
Çap	mm ²		ohm/mt (20°C)		Gr/mt						
6,000	28,26000		0,0417		230,7000						
5,000	19,62500		0,0601		160,2000						
4,500	15,89630		0,0742		129,8000						
4,000	12,56000		0,0939		102,5000						
3,500	9,61630		0,1227		78,4900						
3,250	8,29160		0,1422		67,7000						
3,000	7,06500		0,1669		57,6700						
2,800	6,15440		0,1916		50,2500						
2,500	4,90630		0,2404		40,0500						
2,250	3,97410		0,2968		32,4500						
2,000	3,14000		0,3756		25,6300						
1,900	2,83390		0,4162		23,1400						
1,800	2,54340		0,4637		20,7600						
1,700	2,26870		0,5199		18,5200						
1,600	2,00960		0,5869		16,4100						
1,500	1,76630		0,6677		14,4200						
1,400	1,53860		0,7665		12,5600						
1,300	1,32670		0,8890		10,8300						
1,200	1,13040		1,0654		9,2910						
1,100	0,94990		1,2417		7,7520						
1,000	0,78500		1,5024		6,4100						
0,950	0,70850		1,6647		5,7840						
0,900	0,63590		1,8548		5,1920						
0,850	0,56720		2,0795		4,6300						
0,800	0,50240		2,3475		4,1020						
0,750	0,44160		2,6710		3,6050						
0,700	0,38470		3,0662		3,1410						
0,650	0,33170		3,5560		2,7080						
0,600	0,28260		4,1734		2,3070						
0,550	0,23750		4,9667		1,9390						
0,500	0,19630		6,0097		1,6020						
0,475	0,18090		6,6589		1,4460						
0,450	0,15900		7,4194		1,2980						
0,425	0,13850		8,3179		1,1580						
0,400	0,12560		9,3901		1,0250						
0,375	0,11340		10,6840		0,9009						
0,350	0,09620		12,2650		0,7849						
0,320	0,08040		14,6720		0,6562						
0,300	0,07070		16,6940		0,5767						
0,280	0,06150		19,1640		0,5025						
0,250	0,04910		24,0390		0,4005						
0,240	0,04520		26,0840		0,3691						
0,220	0,03800		31,0420		0,3102						
0,200	0,03140		37,5610		0,2563						
0,190	0,02840		41,6180		0,2314						
0,180	0,02540		46,3710		0,2076						
0,170	0,02270		51,9870		0,1852						
0,160	0,02010		58,6880		0,1641						
0,150	0,01770		66,7740		0,1442						
0,140	0,01540		76,6540		0,1256						
0,130	0,01330		88,9010		0,1083						
0,120	0,01130		104,3300		0,0923						
0,110	0,00950		124,1700		0,0775						
0,100	0,00790		150,2400		0,0641						
0,090	0,00636		185,5769		0,0520						
0,080	0,00503		234,8746		0,0410						
0,070	0,00385		306,7672		0,0314						
0,060	0,00283		417,5561		0,0232						
0,050	0,00196		601,2756		0,0160						
0,040	0,00126		939,4876		0,0103						
0,030	0,00071		1670,2026		0,0058						

çalışma sıcaklığındaki direnci bulmak için "Ct" katsayısı ile 20°C deki ohm direncini çarpınız