

RES-145 23/6 KROM ALÜMİNYUM YUVARLAK TEL

°C Ct	100 1	200 1	300 1,01	400 1	500 1,01	600 1,02	700 1,02	800 1,03	900 1,03	1100 1,04	1200 1,04
Çap	mm²			ohm/mt (20°C)			Gr/mt				
6,000	28,26000			0,0513			200,8000				
5,000	19,62500			0,0738			139,4000				
4,500	15,89630			0,0912			112,9000				
4,000	12,56000			0,1154			89,2100				
3,500	9,61630			0,1507			68,3100				
3,250	8,29160			0,1779			59,2450				
3,000	7,06500			0,2051			50,1800				
2,800	6,15440			0,2355			43,7300				
2,500	4,90630			0,2954			34,8600				
2,250	3,97410			0,3647			28,2300				
2,000	3,14000			0,4615			22,3100				
1,900	2,83390			0,5114			20,1300				
1,800	2,54340			0,5698			18,0700				
1,700	2,26870			0,6388			16,1200				
1,600	2,00960			0,7212			14,2800				
1,500	1,76630			0,8205			12,5500				
1,400	1,53860			0,9419			10,9300				
1,300	1,32670			1,0924			9,4250				
1,200	1,13040			1,2821			8,0320				
1,100	0,94990			1,5256			6,7480				
1,000	0,78500			1,8462			5,5770				
0,950	0,70850			2,0456			5,0330				
0,900	0,63590			2,2793			4,5170				
0,850	0,56720			2,5553			4,0290				
0,800	0,50240			2,8847			3,5690				
0,750	0,44160			3,2822			3,1369				
0,700	0,38470			3,7677			2,7328				
0,650	0,33170			4,3697			2,3554				
0,600	0,28260			5,1283			2,0069				
0,550	0,23750			6,1032			1,6871				
0,500	0,19630			7,3847			1,3942				
0,475	0,18090			8,1826			1,2581				
0,450	0,15900			9,1170			1,1290				
0,425	0,13850			10,2212			1,0069				
0,400	0,12560			11,5389			0,8922				
0,375	0,11340			13,1287			0,7844				
0,350	0,09620			15,0707			0,6830				
0,320	0,08040			18,0297			0,5710				
0,300	0,07070			20,5134			0,5018				
0,280	0,06150			23,5480			0,4372				
0,250	0,04910			29,5396			0,3485				
0,240	0,04520			32,0522			0,3211				
0,220	0,03800			38,1443			0,2699				
0,200	0,03140			46,1545			0,2230				
0,190	0,02840			51,1415			0,2013				
0,180	0,02540			56,9819			0,1807				
0,170	0,02270			63,8818			0,1612				
0,160	0,02010			72,1168			0,1428				
0,150	0,01770			82,0518			0,1255				
0,140	0,01540			94,1941			0,1093				
0,130	0,01330			109,2471			0,0942				
0,120	0,01130			128,2111			0,0803				
0,110	0,00950			152,5814			0,0674				
0,100	0,00790			184,6161			0,0558				

çalışma sıcaklığındaki direnci bulmak için "Ct" katsayısı ile 20°C deki ohm direncini çarpınız